



Miragrid® 10XT

Miragrid® 10XT geogrid is composed of high molecular weight, high tenacity polyester multifilament yarns woven in tension and finished with a PVC coating. Miragrid® 10XT geogrid is inert to biological degradation and resistant to naturally encountered chemicals, alkalis, and acids.

Miragrid® 10XT geogrid is used as soil reinforcement in MSE structures such as segmental retaining walls, precast modular block walls, wire faced walls, geosynthetic wrapped faced walls and steepened slopes. Miragrid® 10XT is also used in MSE stabilized platforms for voids bridging, embankments on soft soils, landfill veneer stability, reducing differential settlement and for foundation seismic stability.

TenCate Geosynthetics Americas is accredited Geosynthetic Accreditation Institute – Laboratory Accreditation Program ([GAI-LAP](#)).

MECHANICAL PROPERTIES	TEST METHOD	UNIT	MINIMUM AVERAGE ROLL VALUE
			MD
Tensile Strength @ Ultimate	ASTM D6637 (Method B)	lbs/ft (kN/m)	9500 (138.6)
Tensile Strength @ 5% strain	ASTM D6637 (Method B)	lbs/ft (kN/m)	3120 (45.5)
Mass/Unit Area ¹	(ASTM D5261)	oz/yd ² (g/m ²)	13.4 (454)
			MINIMUM ROLL VALUE
Creep Rupture Strength ²	ASTM D5262/D6992	lbs/ft (kN/m)	6597 (96.1)
Long Term Design Strength ³		lbs/ft (kN/m)	5712 (83.3)
PHYSICAL PROPERTIES		UNIT	ROLL CHARACTERISTIC
Roll Dimensions ⁴ (width x length)		ft (m)	12 x 200 (3.6 x 61) 12 X 1000 (3.6 x 305)
Roll Area		yd ² (m ²)	267 (220) 1333 (1114)
Estimated Roll Weight		lbs (kg)	223 (102) 1075 (490)
Label Roll Color			WHITE

¹ Minimum Average Roll Values (MARV) shown above are based on QC Testing per a defined lot not to exceed 12 months. Testing Frequency follows ASTM D4354, Table 1.

² 75-year design life based on NTPEP Report [REGEO-2016-01-067](#).

³ Long Term Design Strength for sand, silt, clay. $RF_{CR} = 1.44$; $RF_{ID} = 1.05$; $RF_D = 1.1$ (Installation damage reduction factor for other soils available upon request).

⁴ Special order roll lengths are available upon request

Disclaimer: TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice. Mirafi® is a registered trademark of Nicolon Corporation. Copyright © 2021 Nicolon Corporation. All Rights Reserved

FGS000026
ETQR30