



## Mirafi<sup>®</sup> MPM30

Mirafi<sup>®</sup> MPM30 (PGM-30) is constructed of high strength glass filaments bonded to a polyester fabric. Mirafi<sup>®</sup> MPM (PGM-30) was especially developed for the rehabilitation of asphalt roads.

TenCate Geosynthetics Americas Laboratories are accredited by Geosynthetic Accreditation Institute – Laboratory Accreditation Program ([GAI-LAP](#)).

MECHANICAL PROPERTIES	TEST METHOD	UNIT	MINIMUM AVERAGE ROLL VALUE
Tensile Strength @ 0°	ASTM D5035 (2C-E)	lbs	200
Tensile Strength @ 90°	ASTM D5035 (2C-E)	lbs	200
Tensile Elongation	ASTM D5035	%	< 5
Mass/Unit Area	ASTM D5261	oz/yd <sup>2</sup>	4.0

MECHANICAL PROPERTIES	TEST METHOD	UNIT	MINIMUM TEST VALUE
Melting Point	ASTM D276	F° (C°)	450° (232°)
Asphalt Retention	ASTM D6140	gal/yd <sup>2</sup>	0.10

PHYSICAL PROPERTIES	UNIT	TYPICAL ROLL SIZE
Roll Dimensions (width x length)	ft	10 x 450    12.5 x 360
Roll Area	yd <sup>2</sup>	500
Estimated Roll Weight	lbs	172

Disclaimer: TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice. Mirafi<sup>®</sup> is a registered trademark of Nicolon Corporation. Copyright © 2021 Nicolon Corporation. All Rights Reserved  
FGS000789  
ETQR9